

# TE-FGP20

## BI-AXIAL FIBERGLASS GEOGRID



Titan's TE-FGP fiberglass geogrid is specifically designed for asphalt reinforcement. Its optimal apertures allow asphalt particles to penetrate through the grid to achieve high interlock and effective bonding of the two asphalt lifts. This geogrid is also polymer coated which ensures proper adhesion to the asphalt layers over the tack coat surface, and further optimizes the chemical compatibility between the fiberglass reinforcement and the pavement overlay to create a solid bond of the asphalt layers over the tack coat surface. This bond ensures that the reinforcing grid is in a position to effectively accept and distribute tensile stresses.

It is self-adhesive and offers excellent heat resistance; minimal shrinkage at high temperatures; high chemical, physical and biological durability along with optimal elastic modulus and aperture size. It is biologically unaffected by soil micro-organisms, inert to all chemicals normally found in the soil, and formulated to resist ultraviolet degradation.

TESTED PROPERTY	TEST METHOD	UNIT ENGLISH (METRIC)	VALUE ENGLISH (METRIC)	
			MD	XD
Ultimate Tensile Strength <sup>(1)</sup>	ASTM D-6637	lb/inch (kN/m)	571 (100.0)	1,142 (200.0)
Tensile Strength at 2% strain <sup>(1)</sup>	ASTM D-6637	lb/inch (kN/m)	457 (80.0)	914 (160.0)
Secant Stiffness EA at 2% strain <sup>(1)</sup>	ASTM D-6637	lb/inch (kN/m)	22,847(4,000.0)	45,694 (8000.0)
Shrinkage Properties	Internal Test Method	%	Less than 0.5% at 200°C after 15 minutes	
Strain at Ultimate <sup>(2)</sup>	ASTM D-6637	%	<3	<3
Grid Material			Fiberglass Grid	
Coating			Polymeric with pressure sensitive self-adhesive backing	
Optimum Elasticity Modulus <sup>(2)</sup>		psi (mPA)	10.6 x 10 <sup>6</sup> (73,000)	
Melting Point Coating	ASTM D-276	°f (°C)	662 (>350)	
Melting Point Glass	ASTM C-338	°f (°C)	1508 (>820)	
Aperture Size (center to center of strand)	Nominal	inch (mm)	0.5(12.7)	0.5 (12.7)
Mass/Unit Area <sup>(2)</sup>	ASTM D5261	oz/y <sup>2</sup> (g/m <sup>2</sup> )	18.0 (610)	
<b>TYPICAL ROLL DIMENSIONS</b>				
Roll Length <sup>(3)(4)</sup>	Minimum	ft (m)	246 (75)	
Roll Width <sup>(3)(4)</sup>	Minimum	ft (m)	5.0 (1.5) or 7.3 (2.25)	

Notes:

1. MARV – Minimum Average Roll Values
2. Mean
3. Minimum
4. Typical. Standard roll dimensions are shown. The products may be fabricated to custom lengths to meet customer needs.

Titan Environmental warrants that the geogrid furnished hereunder shall conform to the specification stated herein. Any other warranty including merchantability and fitness for a particular purpose are hereby excluded. If the geogrid does not meet the specification on this page and is notified prior to installation Titan Environmental will replace the geogrid at no additional cost to the customer. Titan Environmental is not responsible for any loss or damage incurred during transit and storage after leaving the manufacturing site. This product specification supersedes all prior specifications for the product described above and is not applicable to any products shipped prior to November 14, 2019.

### TITAN ENVIRONMENTAL CONTAINMENT

Toll Free: 1-866-327-1957 | Email: info@titanenviro.com | Web: www.titanenviro.com

(Rev. April 2020)

**TRUST. QUALITY. VALUE**